

Wallpaper Softener Ready

Product properties

Ready- to-use, effective moisturising agent for removing wallpaper. The consistency allows the softener to be applied in thick layers with longer working time.

- Ready to use
- Efficient



Product use

Used for stripping wallpaper or distemper.

The wallpaper glue is softened, so that the wallpaper can be torn off in big pieces.

Substrate

Must be clean, dry and firm.

Treatment

Remove loose material and paint by cleaning and sanding.

Untreated as well as painted wallpaper can be sanded with coarse sanding paper or a notching device, so that the wallpaper softener can penetrate into the glue.

Application

Roller or brush.

The wallpaper softener is applied in an even and ample layer.

Leave for a few hours, then tear off the wallpaper and scrape down with a wallpaper scraper or spatula.

In case of multiple layers, re-treatment may be necessary.

Any spillage on floors or painted surfaces must be wiped off immediately.

Expected result

Cleaned substrate ready for new treatment.

Please note!

Must not be added the water of the steam wallpaper remover nor be used as pre-treatment in connection with a steam wallpaper remover.

Environmental information

Minimize your paint waste by pre-estimating how much paint you need.

Remove as much paint as possible from tools before cleaning.

Paint and cleaning fluid must not be poured down drains, but collected and disposed of as environmental waste.

Empty and dry packaging should be sorted as plastic, metal handles should be removed and sorted as metal.

Store excess paint correctly so that leftovers can be used and environmental impact is minimised.

Storage

Cool, frost free and tightly closed

Protection equipment

Protect skin and eyes from splashes with suitable clothing, gloves and glasses.
Avoid inhalation of spray mist and grinding dust.
Wear suitable protective equipment, see safety data sheet for further information.

Technical Data

Density (kgs/l)	1.03
Solids Weight %	10.2
Solids Vol. %	7.2
pH	9.3
Nominal spreading rate (m²/ltr.)	4
Long spreading rate (m²/l.)	5
Short Spreading rate (m²/ltr.)	2
Min. working temp. during application and drying/curing	Min. +5°C
Humidity	Max. humidity 80 % RH.
Dilution	Does not usually need to be diluted
Cleaning of Tools etc.	Water
Country of Origin	Denmark

Current TDS Version

January 2025